

1 MG ALLOY INGOTS

CHEMICAL ANALYSIS

ASTM-B94-07

Die Casting	Al	Zn	Mn	Cu	Ni	Fe	Si	Be(ppm)
AM60B	5.5~6.5	≤0.22	0.24~0.60	≤0.010	≤0.002	≤0.005	≤0.10	0.0005~0.0015
AM50B	4.4~5.4	≤0.22	0.26~0.60	≤0.010	≤0.002	≤0.004	≤0.10	0.0008~0.0015
AZ91D	8.3~9.7	0.35~1.0	0.15~0.50	≤0.030	≤0.002	≤0.005	≤0.10	0.0005~0.0015

Aluminum	Mg	Al	Zn	Mn	Cu	Ni	Fe	Si	Pb	Sn	Others	Others
Mg 90/10	90% Min.	9% max	0.25% max	0.25% max	0.10% max	0.01% max	0.05% max	0.20% max	0.01% max	0.01% max	Each 0.05% max	Total 0.30% max

Note:** Other spec. can be analyzed upon request.

INGOT DIMENTION

Size	8Kg (preferably)	12Kg
Length	62cm	64cm
Width	12cm	13cm
Height	6.5cm	9cm

Note*: Other spec. can be analyzed upon request.





PACKAGING & DOCUMENTATION

- Packaging of material: Approx. 1,000kg Mg on wooden pallet covered with waterproof plastic foil, strapped with steel strips.
- Country of Origin: Taiwan/Korea. We provide official documentation: Commercial Invoice, Certificate of Origin, Certificate of Analysis, Packing list, etc.



2 CONTACT US

Please feel free to contact us for any inquiries.

Jorge Bonilla.
jorge@sofeng.com.tw



jorge.sofeng

Address: 4F-9, No. 32, SECTION 1, CHENG GONG ROAD, NANGANG DISTRICT, TAIPEI 115, TAIWAN (R.O.C) Tel: 02-26549393. Fax: 02-26548458.